



Avicel® PH-103 microcrystalline cellulose NF, Ph. Eur., JP

Product Specifications:

Chemical and Physical:

Loss on drying	NMT 3.0 % *
Bulk density	0.26 - 0.31 g/cc
Identification A, B	Passes
Degree of polymerization	NMT 350 units
pH	5.5 - 7.0 *
Conductivity	NMT 75 µS/cm
Residue on ignition	NMT 0.05 %
Water soluble substances	NMT 12.5 mg/5g
Water soluble substances	NMT 0.25 %
Ether soluble substances	NMT 5.0 mg/10g
Heavy metals	NMT 0.001 %
Solubility in Copper Tetrammine Hydroxide	Soluble

Microbiological:

Total aerobic microbial count	NMT 100 cfu/g*
Total yeast and mold count	NMT 20 cfu/g*
Pseudomonas aeruginosa	Absent in a 10g sample
Escherichia coli	Absent in a 10g sample
Staphylococcus aureus	Absent in a 10g sample
Salmonella species	Absent in a 10g sample
Coliform species	Absent in a 10g sample

Additional DuPont Specifications

	D10	D50	D90
Particle size distribution	8-30	36-75	80-175
Particle size (Air Jet):			
wt. % + 60 mesh (250 microns)	NMT 1.0		
wt. % + 200 mesh (75 microns)	NMT 30		

This product meets the requirements for Residual Solvents in the United States Pharmacopeia <467> and complies with the ICH Guide Q3C for Residual Solvents.

*More restrictive than compendium
NLT = Not Less Than
NMT = Not More Than



Product Shelf-life / Re-evaluation Date

Store at ambient conditions. Keep containers sealed; material is very hygroscopic. Re-evaluation date is two (2) years from date of manufacture, if storage conditions stated above are observed. DuPont recommends that after the above re-evaluation date, the customer perform the loss on drying test. Typical Degree Polymerization range for Avicel PH microcrystalline cellulose is 100 to 300.

Safety Data Sheets (SDS) available upon request.

Patents

DuPont or its affiliates is owner and/or licensee of several patents related to its products. The products, processes and uses of such products referred to in this document may be covered by one or more patents or pending applications in the United States and/or other countries. DuPont does not warrant against any infringement claim arising from the sale and/or use of any DuPont product in combination with other materials; the use of any DuPont product in the operation of any process; any DuPont product manufactured to a customer's designs or specifications; or any DuPont product manufactured by any process requested by a purchaser.

Product Suitability

The information contained in this document (as well as any advice or assistance) is provided by DuPont only as a courtesy and is intended to be general in nature. Any uses suggested by DuPont are presented only to assist our customers in exploring possible applications. DuPont make no warranty, express or implied, as to its accuracy or completeness, or the results to be obtained from such information, advice or assistance. Each customer is solely responsible for determining whether the DuPont products are suitable for such customer's intended use, and for obtaining any necessary governmental registrations and approvals for such customer's production, marketing, sale, use and/or transportation of finished goods using or incorporating the DuPont products.

Copyright © 2018 DuPont or its affiliates. All Rights Reserved. The DuPont Oval Logo, DuPont™, Danisco® and all products denoted with ® or ™ are registered trademarks or trademarks of E.I. du Pont de Nemours and Company or its affiliated companies.